

ASTM A 193 Gr.B8A

STAINLESS STEEL

BOLTING MATERIAL FOR LOW TEMPERATURE SERVICE

ASTM A193 Gr.B8A Bolts are manufactured from AISI 304 Stainless Steel carbide solution treated in finished condition. We manufacture these Bolts with great precision & Quality. ASTM A193 Gr.B8A Bolts are also called B8 Stainless Steel bolts, B8 Bolts Etc. Studs, bolts, and other fasteners found in this grade are considered the same as B8 except strain hardened.

Chemical Properties

C	Si	Mn	P	S	Cr	Ni
0.08 Max	1.00 Max	2.00 Max	0.045 Max	0.030 Max	18.0-20.0	8.0-11.0

Mechanical Properties

Yield strength	Tensile strength	Elongation	Reduction	Hardness
Min 0.2% Mpa	Min Mpa	Min %	Min %	HRB Max
205	515	30	50	192

Physical Properties

Density	Elastic Modulus	Mean Coefficient of Thermal			Thermal Conductivity	Specific Heat	Melting Point	
(Kg/m ³)	(Gpa)	Expansion(µm/m/°C)			(W/m.K)	0-100°C	Range F	
8060	193	17.9	18.4	18.8	9.4	12.4	503	1398 To 1454

Equivalent Designation

UNS S30400
 EN number 10088-3
 En name X5CrNi18-10
 W.Nr. 1.4301
 B.S 304 S15 – 304 S31
 AFNOR Z7CN 18-09

CUSTOMER ASSISTANCE : customer@TorqBolt.com

#4/217, Deccan Bank Bldg,
 R. R. Roy Road, Mumbai – 400 004,
 Maharashtra, INDIA

Email: info@TorqBolt.com

Web: www.TorqBolt.com

Copyright 2013 Torqbolt Inc.