

ASTM A 193 Gr.B8MA

STAINLESS STEEL

BOLTING MATERIAL FOR LOW TEMPERATURE SERVICE

ASTM A193 Gr.B8MA Bolts are manufactured from AISI 316 Stainless Steel carbide solution treated with Strain Hardening. We manufacture these Bolts with great precision & Quality. ASTM A 193 Gr.B8MA Bolts are also noted as B8M. Same as B8M except strain hardened, 90,000-125,000PSI Tensile Strength. ASTM A193 Gr.B8MA is similar to B8 fasteners except with added Molybdenum. It has better corrosion resistance than B8. Hex Bolts, studs and other fasteners are common to the B8M spec. It is made from austenitic steels is made from an alloy.

Chemical Properties

C	Si	Mn	P	S	Cr	Mo	Ni
0.08 Max	1.00 Max	2.00 Max	0.045 Max	0.030 Max	16.0-18.0	2.00-3.00	10.0-14.0

Mechanical Properties

Yield strength	Tensile strength	Elongation	Reduction	Hardness
Min 0.2% Mpa	Min Mpa	Min %	Min %	HRB Max
205	515	30	50	192

Heat Treatment

Carbide Solution Treated in the finished condition.

Equivalent Designation

UNS S31600
 EN number 58H,58J
 EN Name X5CrNiMo17-12-2
 Werkstoff.No. 1.4401
 JIS SUS316
 BS 316S31

CUSTOMER ASSISTANCE : customer@TorqBolt.com

#4/217, Deccan Bank Bldg,
 R. R. Roy Road, Mumbai – 400 004,
 Maharashtra, INDIA

Email: info@TorqBolt.com
 Web: www.TorqBolt.com

Copyright 2013 Torqbolt Inc.