

ASTM A 193 Gr.B8MLNA

STAINLESS STEEL

CLASS 1A

BOLTING MATERIAL AS PER ASTM/ASME STANDARDS

ASTM A193 Gr.B8MLNA Class 1A is a lowcarbon, nitrogen-enhanced version of Type 316 molybdenum-bearing austenitic stainless steel. The Type 316 alloys are more resistant to general corrosion and pitting/crevice corrosion than the conventional chromium-nickel austenitic stainless steels such as Type 304. They also offer higher creep, stress-rupture and tensile strength at elevated temperature. The nitrogen in Type 316LN adds additional resistance to sensitization in some circumstances. ASTM A193 Gr. B8MLNA Class 1A are also used for conveying fluids under extreme temperatures in heat transfer process equipment like boilers, heaters, heat exchangers, condensers and others.

Chemical Properties

C	Si	Mn	P	S	Cr	Ni
0.08 Max	1.00 Max	2.00 Max	0.045 Max	0.030 Max	18.0-20.0	8.0-11.0

Mechanical Properties

Yeild strength	Tensile strength	Elongation	Reduction	Hardness
Min 0.2% Mpa	Min Mpa	Min %	Min %	HRB Max
205	515	30	50	90

Heat Treatment

Carbide Solution Treated in the finished condition.

Equivalent Designation

UNS S31653
Din X6 CrNiMoN 17 2 2
Werkstoff.No. 1.4406
Jis sus316
AFNOR Z 2 CND 17.12

CUSTOMER ASSISTANCE : customer@TorqBolt.com

#4/217, Deccan Bank Bldg,
R. R. Roy Road, Mumbai – 400 004,
Maharashtra, INDIA

Email: info@TorqBolt.com

Web: www.TorqBolt.com

Copyright 2013 Torqbolt Inc.