

# A/SA 320M B8M

# STAINLESS STEEL

## CLASS 2

BOLTING MATERIAL FOR LOW TEMPERATURE SERVICE

A/SA 320M covers alloy steel bolting materials for pressure vessels, valves, flanges and fittings for low- temperature service. The term "bolting material" as used in this specification covers rolled, forged, or strain hardened bars, bolts, screws, studs and stud bolts. The bars shall be hot-wrought. A/SA 320M covered several grades, including both ferritic and austenitic steels designated L7, B8, etc. Selection will depend on design, service conditions, mechanical properties and low-tempeerate characteristics. A/SA 320M expressed in both inch-pound units and in SI units. The values stated in either inch-pound units or SI units are to be regarded separately as standard.

### Chemical Properties

C	Si	Mn	P	S	Cr	Mo	Ni
0.08 Max	1.00 Max	2.00 Max	0.045 Max	0.030 Max	16.0-18.0	2.00-3.00	10.0-14.0

### Mechanical Properties

Yield strength	Tensile strength	Elong	Reduction	Hardness
Mpa	Mpa	%	%	HRB
min	min	min	min	max.
655	760	15	45	321

### Heat Treatment

Carbide Solution Treated and Strain Hardened.

### Equivalent Designation

UNS S31600
EN number
EN Name
W.Nr.
SS
AFNOR



CUSTOMER ASSISTANCE : [customer@TorqBolt.com](mailto:customer@TorqBolt.com)

#4/215, Bhatawdekar Lane,  
R. R. Roy Road, Mumbai – 400 004,  
Maharashtra, INDIA

Email: [info@TorqBolt.com](mailto:info@TorqBolt.com)  
Web: [www.TorqBolt.com](http://www.TorqBolt.com)

Copyright 2013 Torqbolt Inc.