

MATERIAL GRADE DATA SHEET

# **ASTM A 320M L70**



BOLTING MATERIAL AS PER ASTM/ASME STANDARDS

ASTM A 320M L70 covers alloy steel bolting materials for pressure vessels, valves, flanges and fittings for low-temperature service. The term "bolting material" as used in this specification covers rolled, forged, or strain hardened bars, bolts, screws, studs and stud bolts. The bars shall be hot-wrought. ASTM A 320M L70 covered several grades, including both ferritic and austenitic steels designated L7, B8, etc. Selection will depend on design, service conditions, mechanical properties and low-tempeerature characteristics. ASTM A 320M L70 expressed in both inch-pound units and in SI units. The values stated in either inch-pound units or SI units are to be regarded separately as standard.

## **ASTM A 320M L70 Chemical Properties**

## **Impact Properties**

С	Si	Mn	P	S	Cr	Мо	Joules	Temperature
0.38-0.48	0.15-0.35	0.75-1.00	0.035 Max	0.040 Max	0.80-1.10	0.15-0.25	27	-73°C

### **ASTM A 320M L70 Mechanical Properties**

Yeild strength	Tensile strength	Elongation	Reduction	
Min 0.2% Mpa	Min Mpa	Min %	Min %	
725	860	16	50	

## **ASTM A 320M L70 Heat Treatment**

Quenched & Tempered @620°C min.

#### **ASTM A 320M L70 Equivalent Designation**

UNS AISI 4140/4142/4145 W.Nr. 1.7225

CUSTOMER ASSISTANCE : customer@TorqBolt.com

Email:info@TorqBolt.com Web: www.TorqBolt.com