

M A T E R I A L G R A D E D A T A S H E E T

SA 453M 668

CLASS B

NICKEL ALLOY

BOLTING MATERIAL FOR HIGH TEMPERATURE SERVICE

SA 453M covers five grades of bolting materials such as grade 660, 651, 662, 665 & 668 with Twelve classes of yield strength ranging from 50 to 120 ksi for use in high-temperature service such as fasteners for pressure vessel and valve flanges. The term "bolting material" as used in SA 453M 668 Class B, covers rolled, forged, or hot-extruded bars; bolts, nuts, screws, washers, studs and stud bolts. SA 453M 668 Class B expressed in both inch-pound units and in SI units. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

Chemical Properties

C	Mn	P	S	Si	Cr	Mo	Ni	V	Ti	Al	B
0.08 Max	2.00 Max	0.040 Max	0.030 Max	1.00 Max	13.5-16.0	1.50 Max	17.5-21.5	0.50 Max	2.20-2.80	0.50 Max	0.001-0.010

Mechanical Properties

Yield strength	Tensile strength	Elongation	Reduction	Hardness		
Mpa	Mpa	%	%	BHN	HRB	HRC
min	min	min	min			
585	895	15	18	248-341	99	37

Heat Treatment

Solution treated @ 980°C hold 1hr,min & liquid quenched and Hardened @ 720°C & 16h air cooled

Equivalent Designation

UNS S66285
W.Nr. 1.4980

CUSTOMER ASSISTANCE : customer@TorqBolt.com

#4/217, Deccan Bank Bldg,
R. R. Roy Road, Mumbai - 400 004,
Maharashtra, INDIA

Email: info@TorqBolt.com
Web: www.TorqBolt.com

Copyright 2013 Torqbolt Inc.