

# SB 564

INCONEL 600

BOLTING M

SB 564 covers nickel alloy forgings. These alloys are classified into different grades according to their chemical composition. Grain size and mechanical properties shall be measured. A tension test and nondestructive ultrasonic test shall be done on each SB 564. The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are for information only and are not considered standard.

## Chemical Properties

C	Mn	S	Si	Cr	Ni	Cu
0.15 Max	1.0 Max	0.015 Max	0.5 Max	14.0-17.0	72.0 Min	0.5 Max

## Mechanical Properties

Yield strength	Tensile strength	Elongation
Mpa	Mpa	%
min	min	min
241	552	30

## Heat Treatment

Solution Annealed @ 1080°C & Liquid Quenched


## Equivalent Designation

UNS N06600
EN number
EN Name
W.Nr. 2.4816
SS
AFNOR

**TorqBolt** Inc

**CUSTOMER ASSISTANCE : [customer@TorqBolt.com](mailto:customer@TorqBolt.com)**

#4/215, Bhatawdekar Lane,  
R. R. Roy Road, Mumbai – 400 004,  
Maharashtra, INDIA



Chemical composition. A chemical analysis shall be performed on each lot of material to determine properties like tensile strength, yield strength, and elongation. SB 564 covers Ni-Cr-Fe alloy UNS N600. Parentheses are mathematical conversions to SI units

Fe
6.0-10.0



Email: [info@TorqBolt.com](mailto:info@TorqBolt.com)

Web: [www.TorqBolt.com](http://www.TorqBolt.com)

Copyright 2013 Torqbolt Inc.