

# F 568M 10.9.3 C

HIGH TENSILE

EXTER

F 568M covers chemical and mechanical requirement for nine property classes of carbon and alloy steel thread diameters. F 568M does not cover dimensional requirements for fasteners of any property class. For procurement purpose, it is mandatory that size, type, style, and any special dimensions of the product for the nine property classes are essentially identical with requirements given for these classes in ISO 898/1. The corrosion resistance and weathering characteristics comparable to those steels covered in Specification

## Chemical Properties

C	Mn	P	S	Si	Cr	Ni
0.14-0.26	0.76-1.39	0.040 Max	0.045 Max	0.13-0.37	0.27-0.53	0.22-0.53

## Mechanical Properties

Yield strength	Tensile strength	Elongation	Re
Mpa	Mpa	%	
min	min	min	
940	1040	9	

## Proof Load Values, kN

Nominal Product Diameter & Thread Pitch						
	M5 X 0.8	M6 X 1	M8 X 1.25	M10 X 1.5	M12 X 1.75	M14 X 2
Method 1	11.8	16.7	30.4	48.1	70.0	95.5
Method 2	13.3	18.9	34.4	54.5	79.2	108

  

M20 X 2.5	M22 X 2.5	M24 X 3	M27 X 3	M30 X 3.5	M36 X 4
-----------	-----------	---------	---------	-----------	---------

203	251	293	381	466	678
230	285	332	431	527	763

M48 X 5	M56 X 5.5	M64 X 6	M72 X 6	M80 X 6	M90 X 6
1220	1680	2220	2870	3600	4640
1380	1910	2520	3250	4080	5250

## Heat Treatment

Quenched & Tempered @ 425°C

## Equivalent Designation

UNS
EN number
EN Name
W.Nr.
SS
AFNOR

**TorqBolt** Inc

CUSTOMER ASSISTANCE : [customer@TorqBolt.com](mailto:customer@TorqBolt.com)

#4/215, Bhatawdekar Lane,  
R. R. Roy Road, Mumbai – 400 004,  
Maharashtra, INDIA



Alloy steel externally threaded metric fasteners in nominal diameters of 1/4" and 3/8". When referencing this specification for diameters other than 1/4" and 3/8", the diameter shall be additionally specified. Requirement for seven of the fasteners shall be in the atmosphere, where as other two classes have atmospheric corrosion resistance per ASTM A 588.

Cu	V
0.17-0.53	0.010 Min

Reduction	Hardness
%	HRC
min	
35	33-39

M16 X 2
130
148

M42 X 4.5
-----------

930
1050

M100 X 6
5800
6570



Email: [info@TorqBolt.com](mailto:info@TorqBolt.com)  
Web: [www.TorqBolt.com](http://www.TorqBolt.com)

Copyright 2013 Torqbolt Inc.