

ASTM F593F

AUSTENITIC STAINLESS STEEL

BOLTING MATERIAL FOR GENERAL PURPOSE USE

ASTM F593F covers the chemical and mechanical requirements for stainless steel bolts, hex cap screws and studs in diameters ranging from 1/4" to 1-1/2" inclusive. These fasteners are for general purpose usage, and are available in seven alloy groups. Below is a basic summary of the common grades within the ASTM F593F specification. A number of other less common grades of ASTM F593F exist, but are not detailed in the description below. The Mechanical table here is limited to Alloy groups 1 and 2, as those are the most common and the Chemical table is only showing the most common alloy grades used for their respective alloy groups

Chemical Properties

Stainless Alloy Group	UNS No.	Composition, % maximum except as shown								
		Carbon	Magnese	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Copper	Molybdenum
2										
316	S31600	0.08	2.00	0.045	0.030	1.00	16.0-18.0	10.0-14.0	-	2.00-3.00
316L	S31603	0.03	2.00	0.045	0.030	1.00	16.0-18.0	10.0-14.0	-	2.00-3.00

Mechanical Properties

Alloy	Marking	Size	Proof Stress	Hardness
2	F593F	1/4 to 1-1/2	30	B65 to 95

Heat Treatment

Machined from annealed or solution annealed stock thus retaining the properties of the original material, or hot-formed solution annealed.

Tensile Stress Areas and Threads Per Inch

Size	Coarse Thread (UNC)		Fine Thread (UNF)		8 Thread series (8 UN)	
	Threads	Stress Area	Threads	Stress Area	Threads	Stress Area
1/4"	20	0.0318	28	0.0364	--	--
5/16"	18	0.0524	24	0.0364	--	--
3/16"	16	0.0775	24	0.0878	--	--
7/16"	14	0.1063	20	0.1187	--	--
1/2"	13	0.1419	20	0.1599	--	--
9/16"	12	0.1820	18	0.2030	--	--
5/8"	11	0.2260	18	0.2560	--	--
3/4"	10	0.3340	16	0.3730	--	--
7/8"	9	0.4620	14	0.5090	--	--
1"	8	0.6060	12	0.6630	--	--
1 1/8"	7	0.7630	12	0.8560	8	0.790
1 1/4"	7	0.9690	12	1.0730	8	1.000
1 3/8"	6	1.1550	12	1.3150	8	1.233
1 1/2"	6	1.4050	12	1.5810	8	1.492

CUSTOMER ASSISTANCE : customer@TorqBolt.com