

INCONEL ALLOY 800HT

NICKEL ALLOY

HIGH TEMPERATURE RESISTING ALLOY

INCONEL ALLOY 800HT having the same basic composition as INCOLOY alloy 800 but with significantly higher creep-rupture strength. The higher strength results from close control of the carbon, aluminum, and titanium contents in conjunction with a high-temperature anneal. Used in chemical and petrochemical processing, in power plants for super-heater and re-heater tubing, in industrial furnaces, and for heat-treating equipment

Chemical Properties

C	Mn	S	Si	Cr	Ni	Cu	Ti	Al	Fe	Al+Ti
0.06-0.10	1.5 Max	0.015 Max	1.0 Max	19.0-23.0	30.0-35.0	0.75 Max	0.15-0.60	0.15-0.60	39.5 Min	0.85-1.20

Mechanical Properties

Yield strength	Tensile strength	Elongation
Min 0.2% Mpa	Min Mpa	Min %
172	448	30

Heat Treatment

Solution Annealed @ 1177°C & Rapidly Liquid Quenched

Equivalent Designation

UNS N08811
En Name X8NiCrAlTi32-21
W.Nr. 1.4959
BS NA 15
AFNOR Z 8 NC 33-21

CUSTOMER ASSISTANCE : customer@TorqBolt.com

#4/217, Deccan Bank Bldg,
R. R. Roy Road, Mumbai - 400 004,
Maharashtra, INDIA

Email: info@TorqBolt.com
Web: www.TorqBolt.com

Copyright 2013 Torqbolt Inc.