

SB 564

INCOLOY 800H

BOLTING M

SB 564 covers nickel alloy forgings. These alloys are classified into different grades according to their chemical composition. Grain size and mechanical properties shall be measured. A tension test and nondestructive ultrasonic test shall be done on each lot. The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are for information only and are not considered standard.

Chemical Properties

C	Mn	S	Si	Cr	Ni	Cu
0.05-0.10	1.5 Max	0.015 Max	1.0 Max	19.0-23.0	30.0-35.0	0.75 Max

Mechanical Properties

Yield strength	Tensile strength	Elongation
Mpa	Mpa	%
min	min	min
172	448	30

Heat Treatment

Solution Annealed @ 1080°C & Liquid Quenched


Equivalent Designation

UNS N08810
EN number
EN Name
W.Nr. 1.4958
SS
AFNOR

TorqBolt Inc

CUSTOMER ASSISTANCE : customer@TorqBolt.com

#4/215, Bhatwdekar Lane,
R. R. Roy Road, Mumbai – 400 004,
Maharashtra, INDIA



Chemical composition. A chemical analysis shall be performed on the material to determine properties like tensile strength, yield strength, and elongation. SB 564 covers Ni-Fe-Cr alloy UNS N600. Parentheses are mathematical conversions to SI units

Ti	Al	Fe
0.15-0.60	0.15-0.60	39.5 Min



Email: info@TorqBolt.com

Web: www.TorqBolt.com

Copyright 2013 Torqbolt Inc.